

TABLE-2

SAMPLE		0.2% Yield Point (20°C) [kg/mm ²]	Tensile Strength (20°C) [kg/mm ²]	Absop. Energy (20°C) [kgfm]	FATT [°C]	500°C - 50kg/mm ² Creep Rupture Time [Hour]
E X A M P L E S	A1	102.3	118.7	22.5	-60	1520
	A2	103.1	121.9	23.9	-57	2430
	A3	103.9	121.4	26.7	-70	2715
	A4	104.9	125.2	21.0	-70	995
	A5	105.0	125.3	22.0	-20	1450
	A6	105.6	125.7	25.8	-35	808
	A7	108.1	121.7	20.7	-27	2058
	A8	107.6	123.7	16.5	-30	3361
COMP EXAM	B1	101.9	114.3	18.0	-35	398
	B2	97.1	115.0	1.6	110	1525
	B3	99.7	116.8	4.2	45	957
	B4	101.2	121.0	26.7	-79	568